

Certificazioni - Certification - Certifications - Zertifizierungen

**PR**

Lamiera preverniciata
 Prepainted sheet
 Tôle laquée
 Vorlackiertes Stahlblech

Test	Prestazione Performance Performance Leistung	Spessore [mm] Thickness Epaisseur Dicke	Normativa di riferimento Reference standards Normes de référence Referenzrichtlinie
Resistenza a trazione - Cross panel tensile strength Résistance à traction - Zugfestigkeit	≥ 80kPa	40 ÷ 200	EN 14509:2013
Resistenza a compressione - Compressive strength Résistance à compression - Druckfestigkeit	≥ 100kPa	40 ÷ 200	EN 14509:2013
Conducibilità termica iniziale Thermal conductivity initial value Conductibilité thermique initiale Anfängliche Wärmeleitfähigkeit	0,023W/mK	40 ÷ 200	EN 14509:2013
Reazione al fuoco* - Reaction to fire* Réaction au feu* - Brandverhalten*	B-s3, d0	40 ÷ 200	EN 14509, EN 13501-1
Permeabilità all'acqua - Water permeability Perméabilité à l'eau - Wasserdurchlässigkeit	B A	60 ÷ 120 150 ÷ 200	EN 14509:2013
Permeabilità all'aria - Air permeability Perméabilité à l'air - Luftdurchlässigkeit	<0,2m³/hm²	40 ÷ 200	EN 14509:2013
Isolamento acustico - Airborne sound insulation Isolation acoustique - Schalldämmung	R _w =25 (-1;-2)dB	40 ÷ 200	EN 14509:2013
Rilascio sostanze pericolose Release of dangerous substances Emission substances dangereuses Freisetzung von gefährlichen Substanzen	Passa Pass Passe Durchgang	40 ÷ 200	EN 14509:2013

*valida per finitura PR - *valid for PR finish - *valable pour la finition PR - *Gültig für Endbearbeitung PR